


TPU ELASTIC TAPE

High quality TPU Elastic that is thin and light with high durability and elasticity. It improves garment products by providing smooth and comfortable edges to the wearer as well improving durability. Trusted by countless brands around the world such as Target, GAP, H&M, and more.

Why choose us?



Thin & light with high transparency



Easy usability in garment production



Crease & wrinkle resistant



100% latex free with no powder or fine dust



Safe to machine wash, dry clean & bleach



Our elastic tape has been tested for 200+ harmful substances and are non-toxic



TPU is recyclable and friendly to the environment

Applications



Trusted & selected by famous brands



ZARA



Walmart

FOREVER 21

Abercrombie & Fitch
TRADEMARK SINCE 1892



Passed trim test by Intertek on the following criteria


- Chemical restriction
- Ph Value
- Stability to washing & dry cleaning
- Color fastness

Needle hole durability test

Brand	Spec	Frequency	Production	Test method
ANYTAPE	6 x 0.08	1,000	Extruding Method	<ol style="list-style-type: none"> 1. Bore 9 sewing holes in 5cm length of the tape 2. Grip both ends at 1 cm inside to each end 3. Repeat 250% elastic extension at the speed of 1,000 mm/min 4. Measure frequency of extension until the needle hole rips off 5. Repeat the same test 3 times and calculate average
	6 x 0.12	1,000		
Japan	6 x 0.12	606	Film Cutting method	
USA	6 x 0.10	175		
Taiwan	6 x 0.08	45		
Korea	6 x 0.08	102		

SPECIFICATIONS

Size chart



Model	Width (mm)	Thickness (mm)	Yards/bag	Meter/bag
JBA-0218	2	0.18	1250	1143
JBA-0312	3	0.12	1300	1189
JBA-0312 BLACK	3	0.12	1300	1189
JBA-0315	3	0.15	1000	914
JBA-0318	3	0.18	850	777
JBA-0412	4	0.12	1000	914
JBA-0412 BLACK	4	0.12	1000	914
JBA-0414	4	0.14	900	823
JBA-0428	4	0.28	405	370
JBA-0508S	5	0.08	1500	1371
JBA-0509	5	0.09	1100	1006
JBA-0509 BLACK	5	0.09	1100	1006
JBA-0512	5	0.12	800	732
JBA-0521	5	0.21	435	398
JBA-0521 BLACK	5	0.21	435	398
JBA-0608S	6	0.08	1400	1280
JBA-0608 BLACK	6	0.08	984	900
JBA-0610TS	6	0.1	900	823
JBA-0612	6	0.12	500	457
JBA-0612 BLACK	6	0.12	650	594
JBA-0615	6	0.15	550	503
JBA-0615 BLACK	6	0.15	550	503
JBA-0621	6	0.21	400	366
JBA-0630	6	0.3	260	238
JBA-0635	6	0.35	215	197
JBA-0812	8	0.12	460	421
JBA-0815	8	0.15	400	366
JBA-10012	10	0.12	385	352
JBA-10016	10	0.16	275	251
JBA-12030	12	0.3	122	112
JBA-20020	20	0.2	110	101



Model	Width (mm)	Thickness (mm)	Yards/bag	Meter/bag
E-0412	3	0.15	500	457
E-0512	3	0.12	500	457
E-0612	2	0.18	1000	914



Model	Width (mm)	Thickness (mm)	Yards/roll	Meter/roll
TP-0612	6	0.12	500	457
TP-0615	6	0.15	500	457
TP-0620	6	0.2	125	114
TP-0627	6	0.27	100	91
TP-10027	10	0.27	100	91
TP-13022	13	0.22	100	91
TP-15016	15	0.16	100	91

Testing

Tested by:



Substance	Standard	Result
LEAD [Pb]	0.2	<0.1
Arsenic [As]	0.2	<0.1
Chrome [Cr total]	1	<0.1
Chrome [Cr VI]	0.5	<0.1
Cobalt [Co]	1	<0.1
Nickel [NI]	1	<0.1
Mercury [Mg]	0.02	<0.01
Copper [Cu]	25	<0.1
Cadmium [Cd]	0.1	<0.01
Antimony [Sb]	30	<0.1

*Tested for 200+ harmful substances. Reports available on request

Properties

Properties	Value
Elongation	300 ~ 500%
Tensile strength	35 MPa